

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 832 848 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:
21.11.2001 Bulletin 2001/47

(51) Int Cl.7: **C01G 49/08, G03G 9/083**

(21) Application number: **97307528.6**

(22) Date of filing: **25.09.1997**

(54) Magnetite particles, a process for producing them and applications thereof

Magnetitteilchen, Verfahren zu deren Herstellung und deren Verwendung

Particules de magnétite, procédé pour sa préparation et son application

(84) Designated Contracting States:
BE DE FR GB IT

(30) Priority: **27.09.1996 JP 27733396**

(43) Date of publication of application:
01.04.1998 Bulletin 1998/14

(73) Proprietor: **TITAN KOGYO KABUSHIKI KAISHA**
Ube-shi Yamaguchi-ken (JP)

(72) Inventors:

- Tokunaga, Hideaki, c/o Titan Kogyo K.K.
Ube-shi, Yamaguchi-ken (JP)
- Wada, Tetsuyuki, c/o Titan Kogyo K.K.
Ube-shi, Yamaguchi-ken (JP)
- Nakamura, Akira, c/o Titan Kogyo K.K.
Ube-shi, Yamaguchi-ken (JP)

(74) Representative: **Colmer, Stephen Gary et al**
Mathys & Squire
100 Gray's Inn Road
London WC1X 8AL (GB)

(56) References cited:
EP-A- 0 566 790 **FR-A- 2 353 619**
GB-A- 2 068 923

- **PATENT ABSTRACTS OF JAPAN** vol. 007, no.
066 (C-157), 18 March 1983 & JP 58 002226 A
(TONE SANGYO KK), 7 January 1983,
- **PATENT ABSTRACTS OF JAPAN** vol. 017, no.
342 (C-1076), 29 June 1993 & JP 05 043253 A
(KANTO DENKA KOGYO CO LTD), 23 February
1993,

Remarks:

The file contains technical information submitted
after the application was filed and not included in this
specification

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 832 848 B1

[0001] This invention relates to magnetite particles that have low residual magnetic flux density, are hexahedral, octahedral or tetradecahedral in shape and that are used as electrophotographic magnetic toners and resin-dispersed carriers, and as black pigments for coatings. The invention also relates to a process for producing such magnetite particles and their applications.

[0002] While various electrostatic copying systems are commercially available today, dry development is performed either by a two-component process using a toner and a carrier or by a one-component process using only a toner. Magnetite is used in most toners and carriers.

[0003] Magnetite particles for use as toners and carriers are required to have various characteristics and particularly those to be used in one-component development are required to have low residual magnetic flux density in order to attenuate the magnetic agglomeration of toner particles. As for the shape of magnetite particles, they are required to be angular as exemplified by hexahedrons in order to provide an enhanced abrasive effect on a photoreceptor to form a satisfactory latent image. Thus, it is desired to provide magnetite particles that have low residual magnetic flux density and which are angular in shape as exemplified by hexahedrons.

[0004] Magnetite particles are known to assume a spherical, hexahedral or octahedral shape depending upon the conditions of their production, particularly the alkali/Fe ratio employed for the generation of the magnetite particles. Spherical magnetite particles generally have low residual magnetic flux density but hexahedrons and polyhedrons having more faces have increased residual magnetic flux density. For example, Japanese Patent Publication No. 201509/1991 proposed hexahedral magnetite particles but they are short of achieving the required low residual magnetic flux density. Japanese Patent Publication No. 144840/1994 proposed substantially hexahedral magnetite particles having blunt, almost planar, ridgelines and they are also short of achieving the required low residual magnetic flux density.

[0005] It has also been proposed that Si, Al and other elements be added to magnetite particles such that they have specified shapes or are improved in dispersibility and heat resistance. For example, Japanese Patent Publication No. 9045/1991 and Japanese Patent Publication No. 92642/1994 proposed that Si be added in order to produce spherical magnetite particles. Japanese Patent Publication No. 286723/1993 teaches an improvement in the dispersibility and heat resistance of magnetite particles by addition of Si and/or Al during and after the formation of magnetite particles. Further, Japanese Patent Publication No. 25747/1996 proposed that Si be allowed to be localized in magnetite particles, thereby reducing their residual magnetism and high electrical resistance. Japanese Patent Publication No. 51538/1993 discloses a high-density, unfogged toner made of octahedral magnetite particles having an uneven distribution of Si. Japanese Patent Publication No. 333594/1993 proposed that Si be localized in magnetite particles to produce a toner of high resolution and density.

[0006] Phosphorus (P) compounds are extensively used in the art of magnetic iron oxides but they have been rarely used in cubic or polyhedral magnetite particles. Conventionally, phosphorus is added to magnetic iron oxides either during the preparation of α -FeOOH or by doping its surface. As an example of the first method, Japanese Patent Publication No. 25546/1964 uses phosphorus in order to retard the growth of crystal nuclei; further, Japanese Patent Publication No. 25202/1983 and Japanese Patent Publication No. 18766/1993 use phosphorus in order to provide an improved particle size distribution. As an example of the second method, USP 3,652,334 teaches the use of phosphorus as an anti-inter agent in thermal conversion to α -Fe₂O₃ and Fe₃O₄. However, all of these examples intend to ensure that the magnetic iron oxides as the final product will have improved dispersibility or that they are improved in shape anisotropy by virtue of the retention of acicularity.

[0007] Phosphorus may be added during the formation of magnetite particles, as taught in Japanese Patent Publication No. 46526/1985; however, this method is intended to produce Co-containing magnetite particles of high coercivity by addition of P together with Co. Thus, no magnetite particles have been known in the art that contain P and Al, and optionally Si, that have low magnetic residual flux density and that are hexahedral, octahedral or tetradecahedral in shape, nor has been known a process for producing such magnetite particles.

[0009] Under these circumstances, the present inventors conducted various studies in order to provide magnetite particles that have desired magnetic characteristics for use as magnetic toners, for example, low residual magnetic flux density but not so low as to sacrifice the saturation magnetic flux density and which are angular enough to ensure the formation of an improved latent image.

[0010] Thus, according to its first aspect, the present invention provides magnetite particles that comprise 0.1 - 5.0 wt% P and 0.1 - 5.0 wt% Al, and optionally up to 5.0 wt% Si, on the basis of Fe and which have a σ /SSA ratio of no more than 0.9 after the application of an external magnetic field of 1 kOe, with σ , denoting residual magnetic flux density and SSA specific surface area.

[0011] In a preferred embodiment, the magnetite particles are hexahedral, octahedral or tetradecahedral in shape. According to its second aspect, the present invention provides a process for producing magnetite particles

by reacting an aqueous ferrous salt solution with an alkali hydroxide to form ferrous hydroxide and subsequently heating it under a stream of an oxygen-containing gas, characterized in that a water-soluble phosphorus compound, a water-soluble aluminum compound and a water-soluble silicon compound are added in amounts of 0.1 - 5.0 wt%, 0.1 - 5.0 wt% and 0 - 5.0 wt% as P, Al and Si, respectively on the basis of Fe to either said alkali hydroxide or aqueous ferrous salt solution or the ferrous hydroxide formed by reacting said two compounds.

[0013] The magnetite particles of the invention which contain P and Al and optionally Si have such low residual magnetic flux density that they can be easily dispersed in binder resins. In addition, the particles are hexahedral, octahedral or tetradecahedral in shape and have high enough abrasive effect on a photoreceptor to form a satisfactory latent image. Hence, the magnetic particles of the invention are advantageous for use as materials for the production of magnetic toners and resin-dispersed carriers.

[0014] The expression σ_r/SSA is used to characterize the magnetite particles of the invention since the residual magnetic flux density σ_r which increases with the specific surface area SSA is preferably compensated by SSA. The magnetite particles of the invention have σ_r/SSA value of no more than 0.9, preferably in the range of 0.5 - 0.9. The residual magnetic flux density σ_r is expressed in emu/g and SSA in m²/g.

[0015] As already mentioned, it is known that either spherical, hexahedral or octahedral magnetite particles are produced depending on the conditions of their synthesis, particles are produced depending on the conditions of their synthesis, particularly the alkali/Fe ratio employed during the reaction for synthesis. It has been found that not only hexahedral and octahedral magnetite particles but also tetradecahedra can be obtained by adding P and Al and optionally Si prior to the start of reaction for the synthesis. The tetradecahedral magnetite particles may be regarded as modified hexahedral or octahedral particles in which their apices have become blunt to a planar form.

[0016] In a particularly preferred embodiment of the invention, the P and Al and optionally Si are incorporated before magnetite crystals form. If P and Al and optionally Si are incorporated after the formation of magnetite particles, the intended magnetite particles, i.e., those which have desired magnetic characteristics for use as magnetic toners, for example, low residual magnetic flux density but not so low as to sacrifice the saturation magnetic flux density and which are hexahedral, octahedral or tetradecahedral in shape, are difficult to produce.

[0017] An important point of the invention is the incorporation of at least P and Al. If P is the sole additive, spherical particles may occasionally form. If Al is the sole additive, goethite particles will also occur during the formation of magnetite particles.

[0018] In the invention, Si may also be incorporated in order to further reduce the residual magnetic flux density.

[0019] The reason why the magnetite particles of the invention should have certain magnetic characteristics, such as low magnetic flux density but not so low as to sacrifice the saturation magnetic flux density, while assuming a hexahedral, octahedral or tetradecahedral form is not completely clear. To the best of the knowledge of the present inventors, P and Al, and optionally added Si would retard the agglomeration of magnetite particles during their growth while causing a certain effect on the growth of magnetite crystal grains such as the inhibition of the growth of a certain crystal face.

[0020] Preferred conditions for the practice of the invention will now be described. The aqueous ferrous salt solution to be used in the invention may be one of ferrous sulfate, ferrous chloride, ferrous nitrate, etc. The alkali hydroxide to be used in the invention may be selected from among hydroxides of alkali metals and alkaline earth metals such as sodium hydroxide, potassium hydroxide and calcium hydroxide, as well as ammonium hydroxide and ammonia gas.

[0021] The alkali hydroxide is preferably used in 0.95 - 1.5 equivalents per Fe²⁺ in the aqueous ferrous salt solution. Below 0.9 equivalents, the desired low residual magnetic flux density is attained but, on the other hand, spherical magnetite particles may form and the intended hexahedral, octahedral or tetradecahedral particles are not easily obtainable. Above 1.5 equivalents, the intended magnetite particles are obtained but not by an industrially feasible method.

[0022] The reaction temperature for oxidizing ferrous hydroxide is preferably in the range of 60 - 100°C. Below 60°C, the saturation magnetic flux density will decrease. Above 100°C, the intended magnetite particles are obtained but not by an industrially feasible method.

[0023] Examples of the water-soluble phosphorus compound to be used in the invention include phosphates such as sodium hexametaphosphate and ammonium primary phosphate, as well as salts of phosphoric acid and phosphorous acid. The water-soluble phosphorus compound is added in 0.1 - 5.0 wt%, preferably 0.1 - 2.0 wt%, as P with respect to Fe. Below 0.1 wt% P magnetite particles having the desired magnetic characteristics such as low residual magnetic flux density but not so low as to sacrifice the saturation magnetic flux density and which are hexahedral, octahedral or tetradecahedral in shape may not be produced.

Above 5.0 wt%, the filtrability of the magnetite particles deteriorates to an industrially unfeasible low level.

[0024] The water-soluble phosphorus compound may be added into the alkali hydroxide, the ferrous salt or the ferrous hydroxide which results upon neutralization reaction of the two compounds. It should however be noted that the water-soluble phosphorus compound should be added before magnetite starts to crystallize.

[0025] Examples of the water-soluble aluminum compound to be used in the invention include aluminum sulfate,

aluminum chloride, aluminum nitrate and sodium aluminate. The water-soluble aluminum compound is added in 0.1 - 5.0 wt%, preferably 0.2 - 2.0 wt% as Al with respect to Fe. Below 0.1 wt% Al magnetic particles which have the desired magnetic characteristics such as low residual magnetic flux density but not so low as to sacrifice the saturation magnetic flux density and which are hexahedral, octahedral or tetradecahedral in shape may not be produced. Above 5.0 wt%, the filtrability of the magnetic particles deteriorates to an industrially unfeasible low level and, what is more, non-magnetic phases such as goethite may form.

[0026] The water-soluble aluminum compound may be added into the alkali hydroxide, the ferrous salt or the ferrous hydroxide which results upon neutralization reaction of the two compounds. It should, however, be noted that the water-soluble aluminum compound should at least be added before magnetic starts to crystallize. Examples of the water-soluble silicon compound to be used in the invention include water glass, sodium silicate, potassium silicate, etc. The water-soluble silicon compound is added in 0 - 5.0 wt%, preferably 0 - 2.0 wt%, as Si with respect to Fe. Above 5.0 wt%, thixotropy will develop and the filtrability of the magnetic particles deteriorates to an industrially unfeasible low level.

[0028] The water-soluble silicon compound may be added into the alkali hydroxide, the ferrous salt or the ferrous hydroxide which results upon neutralization reaction of the two compounds. It should, however, be noted that the water-soluble aluminum compound must at least be added before magnetic starts to crystallize. [0029] While the desired magnetic particles may be produced in the manner just described above, their average size may be adjusted to range from 3 to 25 $\mu\text{m}^2/\text{g}$ in terms of specific surface by selecting appropriate conditions. If magnetic toners are to be eventually produced, the specific surface area ranges desirably from 4 to 15 m^2/g . As long as P and Al and optionally Si are incorporated, the surfaces of the magnetic particles obtained may be treated with Al compounds, Si compounds, Ca compounds or organic compounds such as coupling agents in order to improve the heat resistance and dispersibility of the particles.

[0030] Fig. 1 is an electron micrograph ($\times 50,000$) showing the structure of the P, Al and Si containing magnetic particle prepared in Example 1. The following examples are provided for the purpose of further illustrating the invention but are in no way to be taken as limiting.

[0032] In the Examples and Comparative Examples that follow, various parameters were measured by the methods set forth below. For particle shape determination, the shape of the particles which accounted for at 60% of the particles examined under an electron microscope was determined as the characteristic shape of those sample particles. The specific surface area of particles was measured by the BET method. Residual magnetic flux density was measured with a vibrating-sample magnetometer (VSM = 3 of Toei Kogyo Co., Ltd.) in a maximum applied field of 1 kOe. Saturation magnetic flux density was measured in a maximum applied field of 5 kOe. The P, Al and Si levels of sample particles were measured by fluorescence X-ray analysis with SIMULTICS (fluorescence X-ray analyzer of Rigaku Denki Co., Ltd.). The goethite level of magnetic particles was analyzed by a process comprising dispersing 2.5 g of the sample in 50 mL of 0.05 wt% sodium hexametaphosphate, further dispersing with an ultrasonic homogenizer for 20 min and analyzing the Fe level of the supernatant having goethite dispersed therein.

Example 1

[0033] A reactor was preliminarily charged with 3.86 L of an aqueous NaOH solution (1.67 mol/L) containing 1.49 g of sodium hexametaphosphate (corresponding to 0.25 wt% as P with respect to Fe), 6.77 mL of a sodium aluminate solution (159.5 g/L) (corresponding to 0.60 wt% as Al with respect to Fe) and 1.40 mL of a sodium silicate solution (193.3 g/L) (corresponding to 0.15 wt% as Si with respect to Fe); the reactor was further charged with 2.15 L of an aqueous ferrous sulfate solution containing 1.50 mol/L of Fe^{2+} , whereupon ferrous hydroxide formed (the use of sodium hydroxide corresponded to 1.04 equivalents with respect to Fe^{2+}).

[0034] The resulting ferrous hydroxide was heated at 90°C under mechanical agitation with air being supplied for 120 min at a flow rate of 2 L/min, thereby producing magnetic particles. The resulting particles were washed with water, filtered, dried and comminuted by customary procedures.

[0035] Upon fluorescence X-ray analysis, the comminuted magnetic particles were found to contain P, Al and Si in respective amounts of 0.22 wt%, 0.48 wt% and 0.14 wt% of Fe; they were solely composed of a magnetite phase and had a σ/SSA as low as 0.62. In addition, as is clear from the electron micrograph in Fig. 1, the magnetic particles were tetradecahedral in shape and characterized by a good size distribution.

Examples 2 - 8

[0036] Additional samples of magnetite particles were prepared by repeating the procedure of Example 1, except that the amount of the alkali hydroxide relative to the ferrous salt, the kind of water-soluble phosphorus compound, the amount and timing of its addition, the kind of water-soluble Al compound, the amount and timing of its addition, as well

as the kind of water-soluble Si compound, and the amount and timing of its addition were changed as shown in Table 1. The thus prepared magnetite particles had the characteristics shown in Table 2. Each of the magnetite particles prepared in Examples 2 - 8 was solely composed of a magnetite phase and they were either hexahedral, octahedral or tetradehedral in shape, having low σ_r /SSA values in the range of 0.57 - 0.86.

Comparative Example 1

[0037] A comparative sample of magnetite particles was prepared by repeating the procedure of Example 1, except that neither sodium hexametaphosphate nor sodium aluminate nor sodium silicate were added. The magnetite particles thus obtained were hexahedral in shape but they had a higher σ_r /SSA value (1.06) than the magnetite particles prepared in Example 1.

Comparative Example 2

[0038] An additional comparative sample of magnetite particles was prepared by repeating the procedure of Example 4, except that neither sodium hexametaphosphate nor sodium aluminate nor sodium silicate were added. The magnetite particles thus obtained were octahedral in shape but they had a higher σ_r /SSA value (1.67) than the magnetite particles prepared in Example 4.

Comparative Examples 3 - 7

[0039] Additional comparative samples of magnetite particles were prepared by repeating the procedure of Example 1, except that the amounts of addition of the water-soluble P, Al and Si compounds were respectively changed as shown in Table 1. The thus prepared magnetite particles had the characteristics shown in Table 2.

[0040] The magnetite particles prepared in Comparative Example 3 had a low σ_r /SSA value of 0.68 but they were spherical in shape. The magnetite particles prepared in Comparative Examples 4 and 6 had goethite formed in addition to magnetite. The magnetite particles prepared in Comparative Example 5 were spherical in shape and had a high σ_r /SSA value of 0.99. The magnetite particles prepared in Comparative Example 7 were octahedral in shape but they had a high σ_r /SSA value of 1.23.

Comparative Example 8

[0041] To the magnetite particles prepared in Comparative Example 1, 1.49 g of sodium hexametaphosphate (corresponding to 0.25 wt% as P with respect to Fe), 6.77 mL of a sodium aluminate solution (159.5 g/L) (corresponding to 0.60 wt% as Al with respect to Fe) and 1.40 mL of a sodium silicate solution (193.3 g/L) (corresponding to 0.15 wt% as Si with respect to Fe) and the mixture was washed with water, filtered, dried and comminuted by customary procedures. Upon fluorescence X-ray analysis, the comminuted magnetite particles were found to contain P, Al and Si in respective amounts of 0.22 wt%, 0.48wt% and 0.14 wt% of Fe; however, they had a high σ_r /SSA value of 1.04.

Table 1 - 1

Production of Magnetite Particles										
Run NO.	Alkali addition (in equivalents relative to total Fe ²⁺)	Water-soluble P compound			Water-soluble Al compound			Water-soluble Si compound		
		name	P/Fe, wt%	timing of addition *	name	Al/Fe, wt%	timing of addition *	name	Si/Fe, wt%	timing of addition *
Ex. 1	1.04	sodium hexa-metaphosphate	0.25	A	sodium aluminate	0.60	A	sodium silicate	0.15	A
Ex. 2	1.04	ammonium primary phosphate	0.25	B	aluminum sulfate	0.60	B	do	0.15	B
Ex. 3	1.02	sodium hexa-metaphosphate	0.25	C	sodium aluminate	0.60	C	do	0.15	C
Ex. 4	1.15	do	0.25	A	do	0.60	A	do	0.15	A
Ex. 5	1.04	do	0.50	A	do	0.60	A	do	0.15	A
Ex. 6	1.04	do	0.25	A	do	1.20	A	do	0.15	A
Ex. 7	1.04	do	0.25	A	do	0.60	A	do	0.00	A
Ex. 8	1.04	do	0.50	A	do	0.60	A	do	0.25	A

* A: added to alkali hydroxide

B: added to aqueous ferrous sulfate solution

C: added to aqueous ferrous hydroxide solution

D: added after formation of magnetite particles

Table 1 - 2

Run NO.	Production of Magnetite Particles									
	Alkali addition (in equivalents relative to total Fe ²⁺)	Water-soluble P compound			Water-soluble Al compound			Water-soluble Si compound		
		name	P/Fe, wt%	tim-ing of add-tion *	name	Al/Fe, wt%	tim-ing of add-tion *	name	Si/Fe, wt%	tim-ing of add-tion *
Comp.Ex.1	1.04	-	-	-	-	-	-	-	-	
Comp.Ex.2	1.15	-	-	-	-	-	-	-	-	
Comp.Ex.3	1.04	sodium hexa-metaphosphate	0.25	A	-	-	-	-	-	
Comp.Ex.4	1.04	-	-	-	sodium aluminate	0.60	A	-	-	
Comp.Ex.5	1.04	-	-	-	-	-	sodium silicate	0.15	A	
Comp.Ex.6	1.04	-	-	-	sodium aluminate	0.60	A	do	A	
Comp.Ex.7	1.04	sodium hexa-metaphosphate	0.25	A	-	-	do	0.15	A	
Comp.Ex.8	1.04	do	0.25	D	sodium aluminate	0.60	D	do	D	

* A: added to alkali hydroxide B: added to aqueous ferrous sulfate solution

C: added to aqueous ferrous hydroxide solution

D: added after formation of magnetite particles

Table 2

Run No.	Characteristics of Magnetite particles							
	Shape	Goethite formation wt%	SSA by BET, m ² /g	σ_r^+ , emu/g	σ_s^{++} , emu/g	P/Fe, wt%	Al/Fe, wt%	Si/Fe, wt%
Ex. 1	tetradecahedral	0	10.0	6.2	83.4	0.22	0.48	0.14
Ex. 2	do	0	10.2	5.9	82.5	0.22	0.48	0.14
Ex. 3	hexahedral	0	9.5	6.0	83.7	0.22	0.48	0.13
Ex. 4	octahedral	0	8.5	7.3	82.4	0.21	0.46	0.14
Ex. 5	tetradecahedral	0	9.4	6.2	81.9	0.44	0.48	0.14
Ex. 6	do	0	10.5	7.5	80.7	0.22	1.08	0.14
Ex. 7	do	0	10.4	6.5	83.1	0.22	0.48	0.00
Ex. 8	do	0	10.2	5.9	82.5	0.22	0.48	0.24
Comp.Ex.1	hexahedral	0	9.4	10.0	85.7	0.00	0.00	0.00
Comp.Ex.2	octahedral	0	4.3	7.2	87.2	0.00	0.00	0.00
Comp.Ex.3	spherical	0	8.3	4.2	86.2	0.22	0.00	0.00
Comp.Ex.4	hexahedral	1.7	10.0	6.8	84.3	0.00	0.48	0.00
Comp.Ex.5	spherical	0	9.0	8.9	86.0	0.00	0.00	0.14
Comp.Ex.6	hexahedral	1.1	8.8	6.2	64.4	0.00	0.48	0.14
Comp.Ex.7	octahedral	0	4.6	5.7	87.3	0.22	0.00	0.14
Comp.Ex.8	hexahedral	0	9.5	9.9	83.2	0.22	0.48	0.14

*) Residual flux density measured in external field of 1 kOe:

**) Saturation flux density measured in external field of 5 kOe.

Claims

1. Magnetite particles comprising 0.1 - 5.0 wt% P, 0.1 - 5.0 wt% Al on the basis of Fe and which have a σ_r /SSA ratio of no more than 0.9 after the application of an external magnetic field of 1 kOe, with σ_r denoting residual magnetic flux density and SSA specific surface area.
2. Magnetite particles according to Claim 1 additionally comprising up to 5.0 wt% Si on the basis of Fe.
3. The magnetite particles of Claim 1 or 2 which are hexahedral, octahedral or tetradecahedral in shape.
4. The magnetite particles of any one of Claims 1 - 3, wherein said σ_r /SSA ratio is 0.5 - 0.9.
5. A process for producing magnetite particles by reacting an aqueous ferrous salt solution with an alkali hydroxide to form ferrous hydroxide and subsequently heating it under a stream of an oxygen-containing gas, wherein a water-soluble phosphorus compound and a water-soluble aluminium compound are added in amounts of 0.1 - 5.0 wt% and 0.1 - 5.0 wt% as P and Al, respectively, on the basis of Fe to either said alkali hydroxide or aqueous ferrous salt solution or the ferrous hydroxide formed by reacting said two compounds.
6. A process according to Claim 5 for producing magnetite particles by wherein up to 5.0 wt% on the basis of Fe water-soluble silicon compound is additionally added to either said alkali hydroxide or aqueous ferrous salt solution or the ferrous hydroxide formed by reacting said two compounds.
7. The process of Claim 5 or 6, wherein the amount of the alkali hydroxide relative to said ferrous salt is 0.95 - 1.5 equivalents with respect to Fe^{2+} in said aqueous ferrous salt solution.
8. An electrophotographic magnetic toner comprising the magnetite particles of any one of Claims 1 - 4.
9. A resin-dispersed carrier comprising the magnetite particles of any one of Claims 1 - 4.

Patentansprüche

1. Magnetitteilchen, umfassend 0,1 bis 5,0 Gew.% P, 0,1 bis 5,0 Gew.% Al, in bezug auf Fe, die ein σ_r /SSA-Verhältnis von nicht mehr als 0,9 nach der Anwendung eines externen magnetischen Feldes von 1 kOe aufweisen, wobei σ_r die magnetische Restflussdichte und SSA die spezifische Oberfläche bezeichnen.
2. Magnetitteilchen gemäss Anspruch 1, zusätzlich umfassend bis zu 5,0 Gew.% Si in bezug auf Fe.
3. Magnetitteilchen gemäss Anspruch 1 oder 2, die in ihrer Form hexaedrisch, oktaedrisch oder tetradekaedrisch sind.
4. Magnetitteilchen gemäss einem der Ansprüche 1 bis 3, wobei das σ_r /SSA-Verhältnis 0,5 bis 0,9 beträgt.
5. Verfahren zur Herstellung von Magnetitteilchen durch Umsetzen einer wässrigen Eisensalzlösung mit einem Alkalihydroxid, wobei Eisenhydroxid gebildet wird, und anschliessendem Erhitzen unter einem Strom eines sauerstoffhaltigen Gases, wobei eine wasserlösliche Phosphorverbindung und eine wasserlösliche Aluminiumverbindung in Mengen von jeweils 0,1 bis 5,0 Gew.% und 0,1 bis 5,0 Gew.% als P und Al in bezug auf Fe zu entweder dem Alkalihydroxid oder der wässrigen Eisensalzlösung oder dem Eisenhydroxid, das durch die Umsetzung der zwei Verbindungen gebildet wird, hinzugefügt werden.
6. Verfahren gemäss Anspruch 5 zur Herstellung von Magnetitteilchen, wobei bis zu 5,0 Gew.% in bezug auf Fe einer wasserlöslichen Siliciumverbindung zusätzlich zu entweder dem Alkalihydroxid oder der wässrigen Eisensalzlösung oder dem Eisenhydroxid, das durch Umsetzung der zwei Verbindungen gebildet wird, hinzugefügt wird.
7. Verfahren gemäss Anspruch 5 oder 6, wobei die Menge des Alkalihydroxids relativ zu dem Eisensalz 0,95 bis 1,5 Äquivalente in bezug auf Fe^{2+} in der wässrigen Eisensalzlösung beträgt.
8. Elektrofotografischer magnetischer Toner, umfassend die Magnetitteilchen gemäss einem der Ansprüche 1 bis 4.

9. Harzdispersiertes Trägermaterial, umfassend die Magneteiteilen gemäss einem der Ansprüche 1 bis 4.

Revendicati ns

1. Particules de magnéite comprenant de 0,1 à 5,0 % en poids de P₂ de 0,1 à 5,0 % en poids de Al sur la base du Fe et qui ont un rapport σ/SSA ne dépassant pas 0,9 après l'application d'un champ magnétique externe de 1 kOe, σ , dénotant la densité de flux magnétique résiduel et SSA l'aire spécifique.

2. Particules de magnéite selon la revendication 1 comprenant, en plus, jusqu'à 5,0 % en poids de Si sur la base du Fe.

3. Particules de magnéite selon la revendication 1 ou 2 qui sont de forme hexaédrique, octaédrique ou tétracécaédrique.

4. Particules de magnéite selon l'une quelconque des revendications 1 à 3, dans lesquelles ledit rapport σ/SSA est de 0,5 à 0,9.

5. Procédé de préparation de particules de magnéite comprenant les étapes consistant à faire réagir une solution de sel ferreux avec un hydroxyde alcalin de manière à former un hydroxyde ferreux et à le chauffer par la suite sous un flux de gaz contenant de l'oxygène, dans lequel un composé de phosphore hydrosoluble et un composé d'aluminium hydrosoluble sont ajoutés en des quantités de 0,1 à 5,0 % en poids et de 0,1 à 5,0 % en poids sous forme de P et Al, respectivement, sur la base du Fe, soit audit hydroxyde alcalin, soit à ladite solution aqueuse de sel ferreux ou à l'hydroxyde ferreux formé par la réaction desdits deux composés.

6. Procédé de préparation de particules de magnéite selon la revendication 5 dans lequel jusqu'à 5,0 % en poids, sur la base du Fe, d'un composé de silicium hydrosoluble sont ajoutés en plus, soit audit hydroxyde alcalin, soit à ladite solution aqueuse de sel ferreux ou à l'hydroxyde ferreux formé par la réaction desdits deux composés.

7. Procédé selon la revendication 5 ou 6, dans lequel la quantité de l'hydroxyde alcalin par rapport audit sel ferreux est de 0,95 à 1,5 équivalents par rapport au Fe²⁺ dans ladite solution aqueuse de sel ferreux.

8. Toner magnétique pour l'électrophotographie comprenant les particules de magnéite selon l'une quelconque des revendications 1 à 4.

9. Support dispersé dans une résine comprenant les particules de magnéite selon l'une quelconque des revendications 1 à 4.

Fig. 1



